



**PIPING MATERIAL SPECIFICATION FOR
SRM, IMS, DRS, CNG-PRS & IPRS**

Document No.: GGL/TS/PMS-VMS/PRS/01, REV-00

00	Issued for Approval	
REV. NO	REVISION DESCRIPTION	DATE OF ISSUE

Approved

Table of Contents

1.0	GENERAL	3
2.0	DEFINITIONS	3
3.0	CODES AND STANDARDS	3
4.0	ABBREVIATIONS	5
5.0	GENERAL REQUIREMENT	7

Approved

1. GENERAL

All material shall conform to latest revision of ASTM, API, MSS, BS standards and/or GGL technical specifications. Design and fabrication shall conform to ASME for pressure piping, ASME B 31.8 and ASME B 31.3

Piping Material Specification sheets for different classes, which are part of this specifications, shows materials to be used. Each specification sheet shall be used within its Pressure/Temperature range.

2. DEFINITIONS

Shall	:	This verbal form indicates requirements strictly to be followed in order to confirm to the standards and from which no deviation is permitted
Should	:	This verbal form indicates that among several possibilities one is particularly suitable without mentioning or excluding others or that a certain course of action is preferred but not necessarily required
May	:	This verbal form indicates a course of action permissible within the limits of this standard.
Can	:	This verbal form is used for statements of possibility & capability, whether material, physical or casual

3. CODES AND STANDARDS

The latest revision of the following shall be considered as part of this specification.

- ASME B 16.5 - Steel Pipe Flanges and Flanged Fittings
- ASME B 16.9 - Factory made Wrought Steel Butt welding Fittings
- ASME B 16.10 - Face to Face/ End to End dimension of valves.
- ASME B 16.11 - Forged Steel Fittings, Socket Welding and Threaded
- ASME B 16.20 - Metallic Gaskets for Pipe Flanges.
- ASME B 16.21 - Non-Metallic Flat Gasket for Pipe Flanges
- ASME B 16.25 - Butt welding ends
- ASME B 16.34 - Valves- Flanged, Threaded and welding ends
- ASME B 16.47 - Large Diameter Steel Flanges (26" throu 60")
- ASME B 31.3 - Process Piping
- ASME B 31.4 - Pipeline Transportation system for Liquid hydrocarbons & other Liquids
- ASME B 31.8 - Gas Transmissions and Distribution Piping System
- ASME B 36.10 - Welded and Seamless Wrought Steel Pipe
- ASME B 46.1 - Surface Texture
- API 5L - Line Pipe
- API 6D - Pipeline Valves
- API 590 - Steel Line Blank
- API 600 - Steel Gate Valves Flanges and Butt welding Ends
- API 602 - Steel Gate, Globe, and Check Valves for Sizes NPS 4 (DN 100) and Smaller for the Petroleum and Natural Gas Industries

- BS 1873 - Specification for Steel globe and globe stop and check valves (flanged and butt-welding ends) for the petroleum, petrochemical and allied industries
- BS EN ISO 15761 - Steel gate, globe and check valves for sizes DN 100 and smaller, for the petroleum and natural gas industries
- BS 17292 - Metal Ball valves for Petroleum, Petrochemical and allied industries.
- MSS SP 44 - Steel Pipe line Flanges
- MSS SP 75 - Specification for High Test Wrought Butt Welding Fittings
- MSS SP 97 - Integrally Reinforced Forged Branch Outlet Fitting – Socket Welding, Threaded and Butt welding Ends
- ASTM A 105 - Standard Specification for Carbon Steel Forgings for Piping Applications
- ASTM A 193 - Standard specification for Alloy Steel and Stainless Steel bolting Materials for High temp Service and Other Special Purpose Applications
- ASTM A 194 - Standard Specification for Carbon and Alloy Steel Nuts for Bolts for High Pressure or High Temperature Service or both
- ASTM A 320 - Standard Specification for Alloy-Steel and Stainless Steel Bolting for Low-Temperature Service
- ASTM A 216 - Standard Specification for Steel Casting, Carbon, Suitable for Fusion Welding, for High Temperature Service
- ASTM A 234 - Standard Specification for Piping Fittings of Wrought Carbon Steel and Alloy Steel for Moderate and High Temperature
- ASTM A 285 - Standard Specification for Pressure Vessel Plates, Carbon Steel, Low- and Intermediate-Tensile Strength
- ASTM A 694 - Standard Specification for Carbon and Alloy Steel forgings, for Pipe Flanges, Fitting, Valves and Parts for High Pressure Transmission Service.
- ASTM A 350 - Standard Specification for Carbon and Low-Alloy Steel Forgings, Requiring Notch Toughness Testing for Piping Components ASTM A 420 - Standard Specification for Piping Fittings of Wrought Carbon Steel and Alloy Steel for Low Temperature Service
- ASTM A 860 - Standard Specification for Wrought High Strength Ferritic Steel Butt-Welding Fittings

4. ABBREVIATIONS

4.1 Flange Facing

RTJ	-	Ring Type Joint
FF	-	Flat Face
RF	-	Raised Face

4.2 Fittings

PE	-	Plain End
BE	-	Bevel End
BW	-	Butt Weld
PBE	-	Plain Both End
POE	-	Plain One End
TBE	-	Threaded Both End
TOE	-	Threaded One End
LR	-	Long Radius
SR	-	Short Radius

4.3 Connections

BW	-	Butt-Weld
FLGD	-	Flanged
SCRD	-	Screwed
SO	-	Slip-On
SW	-	Socket Weld
THRD	-	Threaded
WN	-	Weld Neck

4.4 Wall Thickness

SCH	-	Schedule in accordance with ASME B 36.10 or B 36.19
STD	-	Standard Weight Wall Thickness
XS	-	Extra Strong Wall Thickness
XXS	-	Double Extra Strong Wall Thickness

4.5 Valve Description

BC	-	Bolted Cap
BB	-	Bolted Bonnet
ES	-	Extension Stem
FB	-	Full Bore
MO	-	Motor Operated
GO	-	Gear Operated
NRS	-	Non-Rising Stem (with inside screw)
OS&Y	-	Outside Screw and Yoke
RB	-	Reduced Bore
RS	-	Rising Stem
SC	-	Screwed Cap
UB	-	Union Bonnet
UC	-	Union Cap

WB - Welded Bonnet

4.6 Pipes Description

BE - Beveled End
CS - Carbon Steel
ERW - Electric Resistance Welded
EFW - Electric Fusion Welded
FS - Forged Steel
HFI - High Frequency Induction
SAW - Submerged Arc Welded
SMLS - Seamless
NIPL - Pipe Nipple

4.7 Equipment

IMS - Industrial Metering Skid
IPRS - Industrial Pressure Regulating Skid
SRM - Service Regulator Module
CNG-PRS - Compressed Natural Gas- Pressure Regulating Skid
DRS - District Regulating Skid

5. GENERAL REQUIREMENT

All materials shall be inspected and tested as per approved Quality Assurance Plan in accordance with relevant standard/code/GGL specifications.

5.1 PIPE:

- 5.1.1 Pipe dimensions shall be in accordance with API 5L and/or ASME B 36.10 for Carbon Steel pipes.
- 5.1.2 Nominal pipe sizes 1¼", 2½", 3½" and 5" shall not be used except where they are required for specific intended application. When these sizes are used on equipments, the connecting piping shall be increased or decreased to standard sizes as close to equipment as practical.
- 5.1.3 All pipes above 2" shall have bevel ends. 1½" and below piping shall have plain/threaded ends as per relevant standard.
- 5.1.4 Screwed full couplings shall be restricted for instrument connections only (up to 1½").

5.2 FLANGES & FITTINGS

- 5.2.1 Flange bolting shall be fully threaded alloy steel stud bolt with two heavy hex nuts and washer as per the relevant material standard. All CS/AS stud bolts and nuts shall be hot dip galvanized as per ASTM A 153. Stud bolts shall have full continuous threads & lengths shall be ½" longer than that specified in ASME B 16.5 with the provision that a minimum of two thread & maximum of three threads outside each nut & complete with 2 threads to facilitate Stud / bolt tensioning. Stud bolts shall be threaded full length with two heavy hexagonal nuts.
- 5.2.2 Permanent hook eye shall be provided on blinds of weight greater than 60 lbs to facilitate changing of rings.
- 5.2.3 The nuts shall be double chamfered, semi-finished heavy hexagonal type and shall be made by the hot forged process & stamped as per respective material specification.
- 5.2.4 Flange bolts shall be tightened equally and sequentially to impose equal pressure on the gasket and to avoid distortion or over stressing of the equipment.
- 5.2.5 When rating changes occur at flanged joints both the flanges shall be of higher rating if they are of same material.
- 5.2.6 The dimensions of spectacle blinds, spacer and blinds shall be as per ASME B 16.48. Spectacle blinds/spacers and blinds for sizes and rating not available in ASME B 16.48 shall be supplied as per manufacturer standard and design shall be submitted to GGL for review and approval. The corrosion allowance shall be as per the respective class.
- 5.2.7 Special branch fittings and Quick opening closure shall be designed, manufactured, inspected and tested as per ASME B 31.8 code and/or ASME Section VII.
- 5.2.8 All fittings shall be seamless in construction unless and otherwise specified.
- 5.2.9 The thickness of reducing fittings shall match the wall thickness of the higher schedule pipe wall and shall meet the requirement of ASME B 31.8.
- 5.2.10 Fittings shall have at least the same nominal wall thickness as the pipe to which they attach. Welded fittings materials shall be compatible with the piping material.
- 5.2.11 Changes in directions in piping shall normally be made by long radius (LR) butt welded bend in accordance with Piping Material Specification.
- 5.2.12 Cold formed or Miter bends are not permitted.
- 5.2.13 Short radius (SR) welding elbows shall not be used unless absolutely required for clearance purpose. These shall be marked as SR on piping layout drawings and isometrics.
- 5.2.14 Special branch fittings shall be designed, manufactured, inspected and tested as per ASME B 31.8 code.
- 5.2.15 All instrument connections shall be from top or central-horizontal of the header.
- 5.2.16 Gaskets for raised face flanges shall be spiral wound, RPTFE or non-asbestos (CNAF) filled with inner and outer ring with SS 316 in accordance with ASME B 16.20. All spiral wound gaskets shall be supplied with SS outer centering

ring and inner compression ring of SS.

- 5.2.17 All pipe threads, coupling and plug threads shall be NPT in accordance with ASME B 1.20.1.
- 5.2.18 Unless otherwise specified, threaded nipples and caps shall be used for instrument connections and hydrostatic vent & drains and will normally be carbon steel.
- 5.2.19 For Pipe joints of size 1 1/2" & below, SW or threaded fittings shall be used.

5.3 VALVES

- 5.3.1 Vendor shall supply valves in accordance with the valve specification along with auxiliaries, if any, such as gear operated, bypass, sealant injection, vent, drains etc. wherever specified in the specification/data sheets, notes and other enclosures to the requisition. In case of conflict/s between valve specification data sheet, GGL Technical specification and PMS, specification data sheet shall govern.
- 5.3.2 For valves sizes 2" NB and above, notch toughness values shall be determined to provide protection against fracture initiation and propagation. The minimum energy value and shear area shall be as per GGL specification or as per relevant code and standard if not specified in GGL specification.
- 5.3.3 All flanged valves shall have flanges integral (except forged valves) with the valve body. Flange face finish shall be as per ASME B 16.5 unless otherwise specified in GGL valve specification/data sheets.
- 5.3.4 All valves with non-metallic seats and seals shall be fire safe type, Fire safe type test shall be as per API 607/ API 6FA or BS 6755 part-2 (Latest editions) by approved certification body. Fire safe type certificate shall be reviewed by GGL/ TPIA and shall be furnished to the GGL for record.
- 5.3.5 Following requirement of Check valves shall be met over and above the valve specification sheet requirements
- 5.3.5.1 Wherever check valve disc assembly is supported from the cover of check valves the following shall be ascertained.
- Positive location/positioning of cover must be provided to ensure correct alignment of valve disc.
 - Hinge pin design must permit accurate alignment of the disc and valve seat.
- 5.3.5.2 For heavy check valves (50 kg & above), provisions shall be available for lifting by way of lugs, eyebolts and other such standard devices per standard industry practice.
- 5.3.6 If any overlay weld-deposit is used for the body seat ring, seating surface, the seat ring base material shall be at least equal to the corrosion resistance of material of the shell.
- 5.3.7 Soft-seated ball and plug valves shall be supplied with anti-static devices.
- 5.3.8 All ball valves shall be Bi-directional.
- 5.3.9 Ball shall be solid type unless otherwise specified.
- 5.3.10 Body seat shall be renewable type.
- 5.3.11 Ball valve with lubrication fittings, for the ball seats as well as for the stem, shall be provided to prevent the minor leaks or reduce operating torque.
- 5.3.12 Trunion -mounted ball valves shall be supplied with provision for double block and bleed facility.
- 5.3.13 A body bleed port with Globe valve, independent of lubrication fittings shall be provided
- 5.3.14 Gear operated shall be as under, with position indicators for open/close positions, with limit stops (limit stops are not applicable for globe valves)
- | | | |
|------------------|---|---|
| For Globe valves | - | Totally enclosed bevel gear in grease case with grease nipples/plugs |
| For Ball valves | - | Totally enclosed helical worm or combination of helical worm and spur gear in grease case with grease nipples/plugs |
- 5.3.15 Ball valves even with wrench or lever operators shall have Position indicators with limit stops.
- 5.3.16 Wherever lock open (LO) / lock close (LC) specified in the valve Bill of Material, the valve shall be provided with locking arrangement such as pad lock and chain.

- 5.3.17 All valves shall be hydro tested & air tested for body and seat as per respective valve data sheet. The sequence of pressure testing of soft seated valves shall be as follows:

Initially the hydro test for body shall be performed, after this the hydro test for seat shall be done then the low-pressure air test and high pressure pneumatic test shall be performed. In case the valve does not pass the low pressure air test and high pressure pneumatic leakage is observed through the seat, vendor shall replace the seats and entire test sequence is to be repeated to check the soundness of valve.

- 5.3.18 Steel casting of valves shall be 100% radiographed irrespective of rating and size in accordance with ASME B16.34 Mandatory appendices – I.
- 5.3.19 Magnetic particle and Dye penetration testing shall also be done on all castings. Procedure and acceptance criteria shall be as per ASME B16.34 appendices – II and III.
- 5.3.20 For all valve forging, ultrasonic testing and magnetic particle testing shall be carried out as per ASME B16.34 Annexure III & IV.
- 5.3.21 Valve body thickness, wherever not specified in the standard, shall be as per ASME B 16.34. The corrosion allowance shall be considered as 1.6 mm while deriving the design thickness.
- 5.3.22 Socket weld end valves with non-metallic seats or seals shall be provided with nipples (PUP size as per valve datasheet) having materials and thickness equivalent to those specified in the relevant piping specifications. These nipples shall be welded and tested to both ends of the valve by the Manufacturer, before fitting packing, seats and seals. The pipe wall thickness of nipple shall be selected considering the valve body thickness.
- 5.3.23 Stem protection is required for all CS globe valves where 11-13% Cr. trims are specified. The stem shall be totally enclosed in a sleeve, which shall be packed with grease.
- 5.3.24 No cast, ductile or malleable Iron, aluminum, plastic or copper bearing alloy shall be used in Natural Gas service.
- 5.3.25 All material shall be new, clean and free from rust, pits and obvious defects.
- 5.3.26 Material selection for soft seats/seals for Ball valves shall be suitable for maximum differential pressure, corresponding to pressure/temperature rating and service fluid handled on a continuous basis. The seat/seal material in valve data sheets for Ball valves is indicative only. Vendor can propose an alternative seat provided he furnishes the pressure/temperature rating of the proposed seat material which shall cover the class temperature pressure rating of the valve and is superior to the seat/seal material specified in the valve datasheets and subject to GGL approval.

5.4 MARKING:

- 5.4.1 Valve marking, symbols, abbreviations etc. shall be in accordance with API 6D and MSS-SP-25 and/or the standard referred in the specification sheet as applicable. Vendor's name, valve rating, material designation, nominal size, direction of flow (if any) etc. shall be integral on the body.
- 5.4.2 Each valve shall have a corrosion resistant tag giving size, valve tag no. / code no., securely attached to the valve body.
- 5.4.3 Paint or ink for marking shall not contain any harmful metal or metal salt such as zinc, lead or copper which cause corrosive attack on heating.

5.5 DISPATCH:

- 5.5.1 Each end of the valve shall be protected, against ingress of foreign material & damages, with the following materials:

Flange face	:	Wood or plastic cover
Beveled end	:	Wood or plastic cover
SW or Screwed End	:	Plastic cap

- 5.5.2 End protector of wood/plastic to be used on the flange faces shall be attached by at least three bolts and shall not be smaller than the outside diameter of the flange. However the plastic cap for SW & Screwed. End valves shall be press fit type.

5.6 OTHERS:

5.6.1 Flange joints to be kept Minimum.

5.6.2 Globe type valve shall be used for TMBV double block & bleed test.

Approved

GUJARAT GAS LIMITED		PIPING MATERIAL SPECIFICATION FOR SRM, IMS, CNG-PRS, DRS & IPRS					PRESSURE RATING : 150#
							DESIGN PRESSURE : 19 BARG
							TEMPERATURE RANGE : 0°C - 65°C
							LOCATION CLASS : CLASS IV
CODE : ASME B 31.8		SERVICE : NATURAL GAS					CORROSION ALL. : 1.5 MM inclusive
ITEM	SHORT CODE	SIZE FROM-THRU	DESCRIPTION	RATING /SCH. / WT	DIMENSION STANDARD	MATERIAL STANDARD	REMARKS
PIPE	P	1/2" TO 1 1/2"	PE, SEAMLESS	SCH 80	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	PRIMARILY SEAMLESS
		2"	BE, SEAMLESS	SCH 80	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	
		3"	BE, SEAMLESS	SCH 40	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	
		4"	BE, SEAMLESS	SCH 80	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	
		6" TO 12"	BE, SEAMLESS	SCH 40	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	
BALL VALVE	BLV	1/2" – 1 1/2"	SW OR THREADED	800#	BS EN ISO 17292	BODY: ASTM A 105 (Charpy at 0°C) BALL: A351 CF8M/SS316	FLOATING BALL VALVE SOCKET WELD - ASME B 16.11 THREDED - ASME B1.20.1
		2" - 3"	BW OR FLGD (RF 125-250 AARH)	150#	API 6D	BODY: ASTM A 216 Gr. WCB (Charpy at 0°C) BALL: A351 CF8M/SS316	FLOATING BALL VALVE BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5
		4" -12"	BW OR FLGD (RF 125-250 AARH)	150#	API 6D	BODY: ASTM A 216 Gr. WCB (Charpy at 0°C) BALL: A351 CF8M/SS316	TRUNION MOUNTED BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5
GLOBE VALVE	GLV	1/2" – 1 1/2"	SW OR THREADED OR FLGD (RF 125-250 AARH)	800#	BS EN ISO 15761	BODY: ASTM A 105 (Charpy at 0° C) TRIM: SS316	SOCKET WELD - ASME B 16.11 THREDED - ASME B1.20.1. FLANGED END - ASME B 16.5
		2"-4"	BW OR FLGD (RF 125-250 AARH)	150#	API 602/BS 1873	BODY: ASTM A 216 Gr. WCB Charpy at 0° C TRIM: SS316	BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5

		Above 4"	BW OR FLGD (RF 125-250 AARH)	150#	BS 1873	BODY: ASTM A 216 Gr. WCB Charpy at 0° C TRIM: SS316	BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5
LIFT CHECK VALVE	NRV	1/2" – 1 ½"	SW	800#	BS EN ISO 15761	BODY: ASTM A 105 Charpy at 0°C	HORIZONTAL INSTALLATION SOCKET WELD - ASME B 16.11
SWING CHECK VALVE		2" – 12"	BW OR FLGD (RF 125-250 AARH)	150#	API 6D	BODY: ASTM A 216 Gr. WCB Charpy at 0° C	HORIZONTAL INSTALLATION OR VERTICAL INSTALLATION WITH UPWARD FLOW DIRECTION BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5
WAFER TYPE CHECK VALVE		2" & ABOVE	Sandwich Type	150#	API 6D	BODY: ASTM A 216 Gr. WCB Charpy at 0° C	HORIZONTAL INSTALLATION
ELBOWS LR	EL	1/2" – 1 ½"	SW, 1.5 D	3000#	ASME B 16.11	ASTM A 105 Gr. B Charpy at 0° C	SOCKET WELD - ASME B 16.11
		2" - 3"	BW, 1.5 D	M	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
		4" - 12"	BW, 1.5 D	M	ASME B 16.9	ASTM A 234 WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
REDUCERS CONCENTRIC	RC	1/2" – 1 ½"	SW	3000#	ASME B 16.11	ASTM A 105 Gr. B Charpy at 0° C	SOCKET WELD - ASME B 16.11
		2"-3"	BW	MXM	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
		4" - 12"	BW	MXM	ASME B 16.9	ASTM A 234 WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
TEE EQUAL AND REDUCING	T	1/2" – 1 ½"	SW	3000#	ASME B 6.11	ASTM A 105 Charpy at 0° C	SOCKET WELD - ASME B 16.11
		2"-3"	BW	MXM	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
		4" - 12"	BW	MXM	ASME B 16.9	ASTM A 234 WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
SOCKOLET /THREDOLET	S	1/2" to 1 1/2"	SW OR THREADED	3000#	MSS SP 97	ASTM A 105 Charpy at 0° C	SOCKET WELD - ASME B 16.11 THREADED - ASME B1.20.1
WELDOLET	W	2" – 12"	BW	3000#	MSS SP 97	ASTM A 105 Charpy at 0° C	BUTT WELD - ASME B 16.25
END CAP	C	1/2" – 1 ½"	SW	3000#	ASME B 16.11	ASTM A 105 Charpy at 0° C	SOCKET WELD - ASME B 16.11 BUTT WELD - ASME B 16.25
		2" – 12"	BW	M	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	

PIPE NIPPLE	NIPL	1/2" – 1 1/2"	PE, SEAMLESS	SCH 80	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0° C	-
COUPLING (FULL or HALF)	COUP	1/2" – 1 1/2"	SW OR THREADED	3000#	ASME B 16.11	ASTM A 105 Charpy at 0° C	SOCKET WELD - ASME B 16.11 THREADED - ASME B1.20.1
FLANGE	FW	1/2" to 1 1/2"	SORF (125-250 AARH)	150#	ASME B 16.5	ASTM A 105 Charpy at 0° C	
		2"-3"	WNRF (125-250 AARH)	150# Bevel End WT M	ASME B 16.5	ASTM A 105 Charpy at 0° C	2" Socket Weld End flange for Service Regulator Module Only
		4" – 12"	WNRF (125-250 AARH)	150# Bevel End WT M	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
BLIND FLANGE	FB	1/2" to 1 1/2"	RF (125-250 AARH)	150#	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
		2"-3"	RF (125-250 AARH)	150#	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
		4" – 12"	RF (125-250 AARH)	150#	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
SPECTACLE BLIND	FSB	2"-12"	RF (125-250 AARH)	150#	ASME B 16.48	ASTM A 105 Charpy at 0° C	-
STUD & NUT / BOLT	B	1/2" – 12"	-	-	ASME B 18.2	STUD:ASTM A 193 B7 NUT: ASTM A 194 2H ASTM A 153	HOT DIP GALVENIZED
GASKET SPIRAL WOUND	G	1/2" – 12"	-	0.175" THICKNESS	ASME B 16.20	SPIRAL WOUND CNAF FILLER + INNER & OUTER RING SS316	COMPATIBLE WITH ASME B 16.5 FLANGES

NOTE:

1. M = THICKNESS TO MATCH PIPE WALL THICKNESS
2. THIS SPECIFICATIONS SHALL BE READ IN CONJUNCTION WITH GENERAL NOTES AND DATA SHEETS & TECHNICAL SPECIFICATIONS OF AN INDIVIDUAL ITEM

BRANCH TABLE

BRANCH SIZE

HEADER SIZE		1/2"	3/4"	1"	1 ½"	2"	3"	4"	6"	8"	10"	12"
	1/2"	T										
	3/4"	T	T									
	1"	T	T	T								
	1 ½"	T	T	T	T							
	2"	S	S	S	T	T						
	3"	S	S	S	T	T	T					
	4"	S	S	S	T	T	T	T				
	6"	S	S	S	S	W	T	T	T			
	8"	S	S	S	S	W	W	T	T	T		
	10"	S	S	S	S	W	W	T	T	T	T	
	12"	S	S	S	S	W	W	W	T	T	T	T

LEGEND

T : EQUAL/REDUCING TEE
 S : SOCKOLET
 W : WELDOLET

GUJARAT GAS LIMITED		PIPING MATERIAL SPECIFICATION FOR SRM, IMS, CNG-PRS, DRS & IPRS				PRESSURE RATING : 300#	
						DESIGN PRESSURE : 49 BARG	
						TEMPERATURE RANGE : 0°C - 65°C	
						LOCATION CLASS : CLASS IV	
CODE : ASME B 31.8		SERVICE : NATURAL GAS				CORROSION ALL : 1.5 MM inclusive	
ITEM	SHORT CODE	SIZE FROM-THRU	DESCRIPTION	RATING /SCH. / WT	DIMENSION STANDARD	MATERIAL STANDARD	REMARKS
PIPE	P	1/2" TO 1 1/2"	PE, SEAMLESS	SCH 80	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	PRIMARILY SEAMLESS CHARPY TEST AS PER MOC Note: For 12" MAOP is 42 Barg for operating the pipeline at hoop stress below 30%
		2"	BE, SEAMLESS	SCH 80	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	
		3"	BE, SEAMLESS	SCH 40	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	
		4"	BE, SEAMLESS	SCH 80	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	
		8" - 12"	BE, SEAMLESS	SCH 40	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	
BALL VALVE	BLV	1/2" - 1 1/2"	SW OR THREADED	800#	BS EN ISO 17292	BODY: ASTM A 105 (Charpy at 0°C) BALL: A351 CF8M/SS316	FLOATING BALL VALVE SOCKET WELD - ASME B 16.11 THREADED - ASME B1.20.1.
		2" - 3"	BW OR FLGD (RF 125-250 AARH)	300#	API 6D	BODY: ASTM A 216 Gr. WCB (Charpy at 0°C) BALL: A351 CF8M/SS316	FLOATING BALL VALVE BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5
		4" - 12"	BW OR FLGD RF 125-250 AARH	300#	API 6D	BODY: ASTM A 216 Gr. WCB (Charpy at 0°C) BALL: A351 CF8M/SS316	TRUNION MOUNTED BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5
GLOBE VALVE	GLV	1/2" - 1 1/2"	SW OR THREADED	800#	BS EN ISO 15761	BODY: ASTM A 105 (Charpy at 0° C) TRIM: SS316	SOCKET WELD - ASME B 16.11 THREADED - ASME B1.20.1.
		2" - 4"	BW OR FLGD RF 125-250 AARH	300#	BS 1873	BODY: ASTM A 216 Gr. WCB Charpy at 0° C TRIM: SS316	BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5

		Above 4"	BW OR FLGD RF 125-250 AARH	300#	BS 1873	BODY: ASTM A 216 Gr. WCB Charpy at 0° C TRIM: SS316	BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5
LIFT CHECK VALVE	NRV	1/2" – 1 1/2"	SW	800#	BS EN ISO 15761	BODY: ASTM A 216 Gr. WCB Charpy at 0° C	HORIZONTAL INSTALLATION SOCKET WELD - ASME B 16.11
SWING CHECK VALVE		2" – 12"	BW OR FLGD RF 125-250 AARH	300#	API 6D OR BS 1868	BODY: ASTM A 216 Gr. WCB Charpy at 0° C	HORIZONTAL INSTALLATION OR VERTICAL INSTALLATION WITH UPWARD FLOW DIRECTION BUTT WELD - ASME B 16.25 FLANGED END - ASME B 16.5
WAFER TYPE CHECK VALVE		2" & ABOVE	Sandwich Type	300#	API 6D	BODY: ASTM A 216 Gr. WCB Charpy at 0° C	HORIZONTAL INSTALLATION
ELBOWS LR	EL	1/2" – 1 1/2"	SW, 1.5 D	3000#	ASME B 16.11	ASTM A 105 Gr. B Charpy at 0° C	SOCKET WELD – ASME B 16.11
		2"-3"	BW, 1.5D	M	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
		4" - 12"	BW, 1.5 D	M	ASME B 16.9	ASTM A 234 WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
REDUCERS CONCENTRIC	RC	1/2" – 1 1/2"	SW	3000#	ASME B 16.11	ASTM A 105 Gr. B Charpy at 0° C	SOCKET WELD – ASME B 16.11
		2"-3"	BW	M x M	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
		4" - 12"	BW	M x M	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
TEE EQUAL AND REDUCING	T	1/2" – 1 1/2"	SW	3000#	ASME B 6.11	ASTM A 105 Gr. B Charpy at 0° C	SOCKET WELD – ASME B 16.11
		2"-3"	BW	MXM	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
		4" - 12"	BW	MXM	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
SOCKOLET / THREDOLET	S	1/2" - 1 1/2"	SW OR THREADED	3000#	MSS SP 97	ASTM A 105 Charpy at 0° C	SOCKET WELD - ASME B 16.11 THREADED - ASME B1.20.1
WELDOLET	W	2" – 12"	BW	3000#	MSS SP 97	ASTM A 105 Charpy at 0° C	BUTT WELD - ASME B 16.25
END CAP	C	1/2" – 1 1/2"	SW	3000#	ASME B 16.11	ASTM A 105 Gr. B Charpy at 0° C	SOCKET WELD - ASME B 16.11
		2" – 3"	BW	M	ASME B16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
		4" - 12"	BW	M	ASME B 16.9	ASTM A 234 Gr. WPB Charpy at 0° C	BUTT WELD - ASME B 16.25
PIPE NIPPLE	NIPL	1/2" – 1 1/2"	PE, SEAMLESS	SCH 80	ASME B 36.10	ASTM A 106 Gr. B Charpy at 0°C	-

COUPLING (FULL or HALF)	COUP	1/2" – 1 1/2"	SW OR THREADED	3000#	ASME B 16.11	ASTM A 105 Charpy at 0° C	SOCKET WELD - ASME B 16.11 THREADED - ASME B1.20.1
FLANGE	FW	1/2" - 1 1/2"	SORF (125-250 AARH)	300#	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
		2"-3"	WNRF (125-250 AARH)	300# Bevel End WT M	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
		4" - 12"	WNRF (125-250 AARH)	300# Bevel End WT M	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
BLIND FLANGE	FB	1/2" - 1 1/2"	RF (125-250 AARH)	300#	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
		2"-3"	RF (125-250 AARH)	300#	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
		4"-12"	RF (125-250 AARH)	300#	ASME B 16.5	ASTM A 105 Charpy at 0° C	-
SPECTACLE BLIND	FSB	2"-12"	RF (125-250 AARH)	300#	ASME B 16.48	ASTM A 105 Charpy at 0° C	-
STUD & NUT / BOLT	B	1/2" – 12"	-	300#	ASME B 18.2	STUD:ASTM A 193 B7 NUT: ASTM A 194 2H ASTM A 153	HOT DIP GALVENIZED
GASKET SPIRAL WOUND	G	1/2" – 12"	-	0.175" THICKNESS	ASME B 16.20	SPIRAL WOUND CNAF FILLER + INNER & OUTER RING SS316	COMPATIBLE WITH ASME B 16.5 FLANGES

NOTE:

1. M = THICKNESS TO MATCH PIPE WALL THICKNESS
2. THIS SPECIFICATIONS SHALL BE READ IN CONJUNCTION WITH GENERAL NOTES AND DATA SHEETS & TECHNICAL SPECIFICATIONS OF AN INDIVIDUAL ITEM

BRANCH TABLE

Branch Size

HEADER SIZE		1/2"	3/4"	1"	1 1/2"	2"	3"	4"	6"	8"	10"	12"
	1/2"	T										
	3/4"	T	T									
	1"	T	T	T								
	1 1/2"	T	T	T	T							
	2"	S	S	S	T	T						
	3"	S	S	S	T	T	T					
	4"	S	S	S	T	T	T	T				
	6"	S	S	S	S	W	T	T	T			
	8"	S	S	S	S	W	W	T	T	T		
	10"	S	S	S	S	W	W	T	T	T	T	
	12"	S	S	S	S	W	W	W	T	T	T	T

LEGEND

T : EQUAL/REDUCING TEE
 S : SOCKOLET
 W : WELDOLET

Approval Note : PIPING MATERIAL SPECIFICATION FOR SRM, IMS, DRS, CNG-PRS & IPRS

Approval Note Ref. No. : GGL/TS/PMS-VMS/PRS/01, REV-00

Proposed by : Vaibhav Bansal

Proposed On: 08-Dec-2020

Approval details:

Action	Action By	Sign	Date	Remarks
Review	Nikhil Agarwal		08/12/2020 5:24:43 PM	
Review	Ashishkumar Upadhyay		16/12/2020 11:00:31 AM	Dear Nikhil... In attached PMS you included LTCS pipe however no matching fittings and valves mentioned/ included in PMS. Since design temperature range mentioned by you is 0 to 65 degree, there is no need to use LTCS pipe or material. You may either remove LTCS pipe from PMS or include LTCS fitting and valves. Ashish Upadhyay
Review	Nikhil Agarwal		16/12/2020 11:52:52 AM	Removed LTCS material from pipe.
Review	Ashishkumar Upadhyay		16/12/2020 1:20:13 PM	
Review	Jignesh Desai		16/12/2020 3:07:20 PM	Supported
Review	Vinit Goel		17/12/2020 11:37:45 AM	
Review	Chandrakant Vala		17/12/2020 12:58:51 PM	Completed as per supporting Documents
Review	Vijay Pandya		18/12/2020 2:10:40 PM	
Review	Vasudev Gadhavi		18/12/2020 2:11:33	

			PM	
Review	Bharat Patel		30/12/2020 1:01:39 PM	
Review	Ravi Ravipalli		30/12/2020 1:49:34 PM	
Review	Dharmesh Sailor		05/01/2021 11:58:14 AM	
Review	Vipul Randeria		07/01/2021 10:56:15 AM	
Review	Bhasker Joshi		07/01/2021 4:33:13 PM	
Approve	Nagendra Kishore Verma		09/01/2021 12:33:40 PM	

This is a computer-generated document. No signature is required.

Approved



GUJARAT GAS

DATASHEET FOR BALL VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/08

Sr. No.	Description	BALL VALVE		
		Specification		
1. General				
1.1	Valve Size	Below 2”	2” and 3”	4" and above
1.2	Pressure Rating	800#	150# / 300#	150#/300#
1.3	Design Standard	BS EN ISO 17292	API 6D (latest)	API 6D (latest)
1.4	Corrosion allowance	1.5 mm	1.5 mm	1.5 mm
1.5	Design Factor	0.4	0.4	0.4
2. Service Conditions				
2.1	Service	Natural Gas	Natural Gas	Natural Gas
2.2	Design Pressure	138 Bar-g	1. For 150# - 19 Bar-g 2. For 300# - 49 Bar-g	1. For 150# - 19 Bar-g 2. For 300# - 49 Bar-g
2.3	Design Temperature	0°C to 65°C	0°C to 65°C	0°C to 65°C
2.4	Operating Pressure Maximum	19 Bar-g for 150# application 49 Bar-g for 300# application	19 Bar-g for 150# application 49 Bar-g for 300# application	19 Bar-g for 150# application 49 Bar-g for 300# application
2.5	Operating Temperature	0°C to 50°C	0°C to 50°C	0°C to 50°C
3. Valve Construction Design				
3.1	Location	Above Ground	Above Ground	Above Ground
3.2	Valve Type	Floating	Floating	Trunion mounted
3.3	Bore Type	Full Bore	Full Bore	Full Bore
3.4	End Connections	1. Socket welded as per ASME B 16.11 2. Threaded as per ASME B 1.20.1	1. Flange End Raised Face (as per ASME B 16.5) 2. Butt Welded (as per ASME B 16.25)	1. Flange End (as per ASME B16.5) 2. Butt Welded (as per ASME B16.25) 3. Ring Type (as per ASME B 16.5)
3.5	PUPS Length	1. Length - 150mm (Max.) 2. Bevel angel as per ASME B 31.8 Note: Thickness of pup shall be as per piping Material specification	1. Length - 150mm (Max.) 2. Bevel angel as per ASME B 31.8 Note: Thickness of pup shall be as per piping Material specification	1. Length-1.5 x ND or 300mm (Min.) and 800mm (Max.) 2. Bevel angel as per ASME B 31.8



GUJARAT GAS

DATASHEET FOR BALL VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/08

3.6	Locking Arrangement	Required - Locking facility in full open position	Required - Locking facility in full open position	Required - Locking facility in full open position
3.7	Shutoff Class	Class: VI	Class: VI	Class : VI
3.8	Construction	Two or Three Piece construction / Bolted	Two or Three Piece construction required/Bolted	Two or Three Piece construction /Bolted
3.9	Bi-Directional	Required	Required	Required
3.10	Double Block and Bleed	Not Required	Not Required	Required
3.11	Blowout Proof Stem	Required	Required	Required
3.12	Anti-Static Device	Required	Required	Required
3.13	Valve Operation	Lever Operated with PVC Grip	Lever operation with PVC Grip	4" lever operated & Gear operated for size 6" and above for 150# and 300#
3.14	Open & Close Ball Position Indicator	Required	Required	Required
3.15	Flange Facing	-	RF-125 AARH (ASME B 16.5)	RF-125 AARH (ASME B 16.5)
4. Valve Material Specification (Equivalent Or Superior)				
	Part	Specified Material	Specified Material	Specified Material
4.1	Body	ASTM A 105 (Charpy test at 0°C)	ASTM A 216 Gr WCB (Charpy test at 0°C)	ASTM A 216 Gr WCB (Charpy test at 0°C)
4.2	Ball (SOLID)	ASTM A479 Gr. SS 316 / ASTM A 351 Gr. CF8M	ASTM A 479 Gr. SS316 / ASTM A351 Gr.CF8M	ASTM A 479 Gr. SS316 / ASTM A351 Gr.CF8M
4.3	Primary seat	Seat: RPTFE OR Superior	ASTM A 479 Gr. SS316 / ASTM A351 Gr.CF8M	ASTM A 479 Gr. SS316 / ASTM A351 Gr.CF8M
4.4	Seat insert		For 150# & 300# : RPTFE OR Superior	For 150# & 300# : RPTFE OR Superior
4.5	Stem (Anti-Blow Out) (No Casting)	ASTM A479 Gr. SS316 / ASTM A 182 Gr. F51 / ASTM A 564 Type 630 (17 – 4PH)	ASTM A479 Gr. 316 OR ASTM A Gr.F316 OR ASTM A 564 Type 630 (17-4PH)	ASTM A479 Gr. 316 / ASTM A 182 Gr. F51 / ASTM A 564 Type 630 (17 – 4PH)
4.6	Stem seals (Renewable with valve open on Stream)	-	GRAFOIL OR RPTFE V-Rings OR Viton	GRAFOIL OR RPTFE V-Rings OR Viton



GUJARAT GAS

DATASHEET FOR BALL VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/08

4.7	Pups	1. MOC-ASTM A 106 Gr. B (Charpy test at 0 Deg C) 2. The carbon content is greater than 0.12% in product analysis, the CE (IIW) shall not exceed 0.40% and if carbon content is less than 0.12% in product analysis, the CE (Pcm) shall not exceed 0.20%.	1. MOC-ASTM A 106 Gr. B (Charpy test at 0 Deg C) 2. The carbon content is greater than 0.12% in product analysis, the CE (IIW) shall not exceed 0.40% and if carbon content is less than 0.12% in product analysis, the CE (Pcm) shall not exceed 0.20%.	1. MOC-ASTM A 106 Gr. B (Charpy test at 0 deg C) or ASTM A 333 Gr. 6, WT matching to pipe WT as per Piping Material Specification. 2. The carbon content is greater than 0.12% in product analysis, the CE (IIW) shall not exceed 0.40% and if the carbon content is less than 0.12% in product analysis, the CE (Pcm) shall not exceed 0.20%.
4.8	Stud and Nuts	Stud-ASTM A 193 Gr. B7 and Nut ASTM A 194 Gr. 2H, Hot Dipped Galvanized as per ASTM A 153	Stud-ASTM A 193 Gr. B7 and Nut ASTM A 194 Gr. 2H, Hot Dipped Galvanized as per ASTM A 153	Stud-ASTM A 193 Gr. B7 and Nut ASTM A 194 Gr. 2H, Hot Dipped Galvanized as per ASTM A 153
4.9	Anti-Static Device	SS302	SS 302	SS 302
4.10	Gland Packing	GRAFOIL	GRAFOIL	GRAFOIL
4.11	Body Gasket	-	Spiral Wound with inner & outer ring SS 316 with CNAF fill	Spiral Wound with inner & outer ring SS 316 with CNAF Filler
4.12	Gear Box	-	-	Material : CS OR MS Quarter Turn Worm Type Protection against water ingress Self Locking provision required
4.13	Stem & Seat Sealant Injector	-	Not Required	-
4.14	Drain & Vent (For 6" NB & above) (Drain only for 4" NB)	-	-	Configuration : One (1) Ball valve + One (1) Needle valve + De pressurizing Plug Valve, pipe & Plug MoC : SS 316 Valve, pipe Size & Plug : ½" NB for 4" NB to 8" NB and 1" NB for 8" NB above Pipe Thickness as per GGL Piping Material Specification



GUJARAT GAS

DATASHEET FOR BALL VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/08

4.15	Stem & Seat Sealant Injector(For size 6" NB and above)	-	-	Configuration – Needle valve with internal NRV and PlugValve & pipe MOC : SS 316 Note: Stem & sealant injector required for 4" NB extended stem valves
5. Valve Testing Requirement				
5.1	Fire Resistant Design Requirement	As per API 6FA/API 607 / BS : 6755 (Part - II) BS EN ISO 10497/API-RP-6FA/API 602	As per API 6FA/API 607/BS:6755 (Part – II)/BS EN ISO 10497	As per API 6FA/API 607 / BS : 6755 (Part – II) BS EN ISO 10497/API-RP-6FA
5.2	Double block and Bleed Test	-	-	Required
5.3	Closure Test	-	-	-
5.4	Hydrostatic Test	Body: 1.5 X Design Pressure Seat: 1.1 X Design Pressure	Body: 1.5 X Design Pressure Seat: 1.1 X Design Pressure	Body: 1.5 X Design Pressure Seat: 1.1 X Design Pressure
5.5	Air Seat Test	7 Bar-g	7 Bar-g	7 Bar-g
5.6	Anti-Static Testing Requirement	Direct current <12V and resistance on dry valves shall not exceed 10 Ohms	Direct current <12 V and resistance on dry valves shall not exceed 10 Ohms	Direct current <12 V and resistance on dry valves shall not exceed 10 Ohms
5.7	Charpy Impact Test	Body & side pieces, Pipe pup, vent drain pipe, Ball & seat, Stem and all pressure containing part as per the MOC standard In case Charpy test value not specified in relevant codes and standards than Charpy shall be carried out at 0 °C and absorbed energy value shall be average 27 J and minimum 22 J respectively .	Body & side pieces, Pipe pup, vent drain pipe, Ball & seat, Stem and all pressure containing part as per the MOC standard In case Charpy test value not specified in relevant codes and standards than Charpy shall be carried out at 0 °C and absorbed energy value shall be average 27 J and minimum 22 J respectively.	Body & side pieces, Pipe pup, vent & drain pipe, Ball & seat, Stem and all pressure containing part as per the MOC standard. In case Charpy test value not specified in relevant codes and standards than Charpy shall be carried out at 0 °C and absorbed energy value shall be average 27 J and minimum 28 J respectively.
5.8	Hardness test	Applicable as per Material of construction standard	Applicable as per Material of construction standard	Applicable as per Material of construction standard
5.9	NDE Test	As per notes	As per notes	As per notes



GUJARAT GAS

DATASHEET FOR BALL VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/08

5.1	Operational Torque Test	-	As per API 6D	As per API 6D
5.11	Marking & Painting	SSPC-SP/MSS SP-25, API 6D and as per GGL Technical Specification	SSPC-SP/MSS SP-25, API 6D and as per GGL Technical Specification	SSPC-SP/MSS SP-25, API 6D and as per GGL Technical Specification

Note:

1. This data sheet shall be read in conjunction with SOR, Technical Specifications and Piping Material Specification.
2. Inspection and Testing: As per this Data Sheet, GGL Specification, API 6D and API 598. Inspection shall be carried out by TPI at Manufacture's work as per QAP approved by GGL.
3. Short pattern ball valves are not acceptable.
4. Vendor to submit GA drawing and QAP for approval prior to commencement of manufacturing.
5. Test Certificates shall be reviewed by client/TPIA as per approved QAP, GA drawing, Inspection & Test certificates including NDE.
6. In case valve is supplied in accordance with API 6D/ BS EN ISO 15761/API 602, Min. body valve thickness shall be as per ASME B 16.34 and corrosion allowance.
7. 100% of valve shall undergo hydro test of seat, soft seat shall be replaced after hydro test in case the same is found damaged or un-serviceable. After that all ball valves shall be air tested.
8. Vendor to submit suitable type of corrosion protection coating system for Underground and above ground valve for salient atmosphere for GGL approval prior to commencement of work along with GA drawing.
9. TPIA shall issue EN 10204 3.1/3.2 certification for testing & inspection of valves
10. Vendor shall provide ball valve weight and operation torque requirement in GAD for reference.
11. Vendor to provide suitable provision for valve lifting and valve support. The same shall be shown in valve GAD.
12. Vent, Drain and sealant connection with valve body shall be of socket welded type. Threaded connection not acceptable for vent, drain and sealant connections.
13. Painting and coating of valve shall be as per technical specifications for valves.
14. Primary seat Metal to Metal and secondary seat shall be soft type for ball valve having size 4" and Above.
15. Non Destructive Examination
 - All sizes, body casting shall be subjected to 100% radiography as per ASME B 16.34. Procedure and acceptance criteria shall be as per ASME B 16.34.
 - All forgings shall be ultrasonically examined in accordance with the procedure and acceptance standard of Annexure E of ASME B 16.34.



DATASHEET FOR BALL VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/08

- Full inspection by radiography shall be carried out on all welds of pressure containing parts. Acceptance criteria shall be as per ASME B 31.3 or ASME B31.8 as applicable and API 1104.
- All finished weld ends subject to welding in field shall be 100% ultrasonically tested for lamination type defects for a distance of 50 mm from the end. Laminations shall not be acceptable.
- Weld ends of all cast valves subject to welding in field shall be 100% radio graphically examined and acceptance criteria shall be as per ASME B16.34.
- After final machining, all bevel surfaces shall be inspected by dye penetrate or wet - magnetic particle methods. All defects longer than 6.35 mm shall be rejected. Reject able defects must be removed.
- Weld repair of bevel surface is not permitted.



GUJARAT GAS

DATASHEET FOR GLOBE VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/07

Sr. No.	Description	GLOBE VALVE	
		Specification	
1. General			
1.1	Valve Size	Below 2”	2” TO 12”
1.2	Pressure Rating	800#	150#/300#
1.3	Design Standard	BS EN ISO 15761 / API 602	API 602 / BS 1873 / ASME B 16.34
1.4	Corrosion allowance	1.5 mm	1.5 mm
1.5	Design Factor	0.4	0.4
2. Service Conditions			
2.1	Service	Natural Gas	Natural Gas
2.2	Design Pressure	138 Bar-g	1. For 150# - 19 Bar-g 2. For 300# - 49 Bar-g
2.3	Design Temperature	0°C to 65°C	0°C to 65°C
2.4	Operating Pressure Maximum	19 Bar-g for 150# application 49 Bar-g for 300# application	19 Bar-g for 150# application 49 Bar-g for 300# application
2.5	Operating Temperature	0°C to 50°C	0°C to 50°C
3. Valve Construction Design			
3.1	Location	Above Ground	Above Ground
3.2	Bore Type	Full Bore OR Reduced Bore	Full Bore OR Reduced Bore
3.3	End Connections	Socket Weld End (as per ASME B 16.11) Threaded End (as per ASME B 1.20.1)	1. Flange End Raised Face (as per ASME B 16.5) 2. Butt Welded (as per ASME B 16.25)
3.4	Locking Arrangement	Not Applicable	Not Applicable
3.5	Shutoff Class	Class: VI	Class: VI
3.6	Construction	-	Bolted Type
3.7	Valve Operation	Hand wheel operated (Rising stem type)	Hand wheel operated (Rising type)
3.8	Open & Close Ball Position Indicator	Required	Required



GUJARAT GAS

DATASHEET FOR GLOBE VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/07

3.9	Screw Type / Stem	OS & Y, Rising stem, Stem protection is required	OS & Y, Rising stem, Stem protection is required
3.10	Flange Facing	-	RF-125 AARH (ASME B 16.5)
4. Valve Material Specification (Equivalent Or Superior)			
	Part	Specified Material	Specified Material
4.1	Body	ASTM A 105 (Charpy test at 0°C)	ASTM A 216 Gr WCB (Charpy test at 0°C)
4.2	Stem (Anti-Blow Out) (No Casting)	ASTM A 479 Gr. SS 316 (No casting) / ASTM A 182 Gr. F316	ASTM A 479 Gr. SS 316 (No casting) / ASTM A 182 Gr.F316
4.3	Disc (Plug type)	ASTM A 479 Gr. SS 316 –Stellited	ASTM A 479 Gr. SS 316 – Stellited
4.4	Disc Nut	ASTM A 479 Gr. SS 316	ASTM A 479 Gr. SS 316
4.5	Disc Seat Ring	ASTM A 479 Gr. SS 316 –Stellited	ASTM A 479 Gr. SS 316 – Stellited
4.6	Gland / Gland Flange	ASTM A 479 Gr. SS 316	Gland: ASTM A 479 Gr. SS 316
4.7	Gland Packing	Grafoil	Grafoil
4.8	Stem seals (Renewable with valve open on Stream)	As per Manufacturer's recommendation	As per Manufacturer's recommendation
4.9	Stud and Nuts	Stud-ASTM A 193 Gr. B7 and Nut ASTM A 194 Gr. 2H, Hot Dipped Galvanized as per ASTM A 153	Stud-ASTM A 193 Gr. B7 and Nut ASTM A 194 Gr. 2H, Hot Dipped Galvanized as per ASTM A 153
4.10	Body Gasket	Spiral Wound with inner & outer ring SS 316 with CNAF fill	Spiral Wound with inner & outer ring SS 316 with CNAF fill
4.11	Seat and Back Seat arrangement	Renewable type	Renewable type
4.12	Hand Wheel	Carbon steel/Mild Steel with suitable Grip with suitable coating & painting	Carbon steel/mild steel with suitable Grip and with suitable coating & painting
5. Valve Testing Requirement			
5.1	Fire Resistant Design Requirement	As per API 6FA/API 607/BS:6755 (Part – II)/BS EN ISO 10497 / API 602	As per API 6FA/API 607/BS:6755 (Part – II)/BS EN ISO 10497



DATASHEET FOR GLOBE VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/07

5.2	Closure Test	High Pressure- 1.1 x Design Pressure (Water) Low Pressure- 7 Bar-g (Air)	High Pressure- 1.1 x Design Pressure (Water) Low Pressure- 7 Bar-g (Air)
5.3	Hydrostatic Test	Body: 1.5 X Design Pressure Seat: 1.1 X Design Pressure	Body: 1.5 X Design Pressure Seat: 1.1 X Design Pressure
5.4	Back Seat Test	High Pressure- 1.1 x Design Pressure (Water) Low Pressure- 7 Bar-g (Air)	High Pressure- 1.1 x Design Pressure (Water) Low Pressure- 7 Bar-g (Air)
5.5	Charpy Impact Test	Required for all pressure containing part as per the MOC standard. In case Charpy test value not specified in relevant codes and standards than Charpy shall be carried out at 0 °C and absorbed energy value shall be average 35 J and minimum 28 J respectively.	Required for all pressure containing part as per the MOC standard. In case Charpy test value not specified in relevant codes and standards than Charpy shall be carried out at 0 °C and absorbed energy value shall be average 35 J and minimum 28 J respectively.
5.6	Hardness test	Applicable as per Material of construction standard	Applicable as per Material of construction standard
5.7	NDE Test	As per notes	As per notes
5.8	Marking & Painting	SSPC-SP/MSS SP 25 /BS EN ISO 15761/API 602 As per GGL Technical Specification	SSPC-SP/MSS SP 25 /BS EN ISO 15761/API 602 As per GGL Technical Specification

Note:

1. This data sheet shall be read in conjunction with SOR, Technical Specifications and Piping Material Specification.
2. Inspection and Testing: As per this Data Sheet, GGL Specification and applicable standards. Inspection shall be carried out by TPI at Manufacture's work as per QAP approved by GGL.
3. Vendor to submit GA drawing and QAP for approval prior to commencement of manufacturing.
4. Test Certificates shall be reviewed by client/TPIA as per approved QAP, GA drawing, Inspection & Test certificates including NDE.
5. In case valve is supplied in accordance with API 6D/ BS EN ISO 15761/API 602, Min. body valve thickness shall be as per ASME B 16.34 and corrosion allowance.
6. 100% of valve shall undergo hydro test of seat. After that all ball valves shall be air tested.

Document No.: GGL/TS/2021/JAN/07

7. Vendor to submit suitable type of corrosion protection coating system for Underground and above ground valve for salient atmosphere for GGL approval prior to commencement of work along with GA drawing.
8. TPIA shall issue EN 10204 3.1/3.2 certification for testing & inspection of valves
9. Vendor to provide suitable provision for valve lifting and valve support. The same shall be shown in valve GAD.
10. Painting and coating of valve shall be as per technical specifications for valves.
11. Vendor to mentioned weight of Globe valve in GAD for reference.
12. Globe Valve Shell Test Duration:
 - Below 2" : 15 Second
 - 2" to 6" : 60 Second
 - 8" & Above : 120 Second
13. Globe Valve Closure Test Duration:
 - Below 2" : 15 Second
 - 2" to 6" : 30 Second
 - 8" & Above : 60 Second
14. Non Destructive Examination:
 - For all sizes, body casting shall be subjected to 100% radiography.
 - Body castings of all valves shall be 100% radio graphically examined as per ASME B16.34. Procedure and acceptance criteria shall be as per ASME B 16.34. All forgings shall be ultrasonically examined in accordance with the procedure and acceptance standard of Annexure E of ASME B 16.34.
 - All forgings shall be ultrasonically examined in accordance with the procedure and acceptance standard of Annexure E of ASME B 16.34.
 - Full inspection by radiography shall be carried out on all welds of pressure containing parts. Acceptance criteria shall be as per ASME B 31.3 or ASME B31.8 as applicable and API 1104.
 - All finished weld ends subject to welding in field shall be 100% ultrasonically tested for lamination type defects for a distance of 50 mm from the end. Laminations shall not be acceptable.
 - Weld ends of all cast valves subject to welding in field shall be 100% radio graphically examined and acceptance criteria shall be as per ASME B16.34.
 - After final machining, all bevel surfaces shall be inspected by dye penetrate or wet - magnetic particle methods. All defects longer than 6.35 mm shall be rejected. Reject able defects must be removed.
 - Weld repair of bevel surface is not permitted.



GUJARAT GAS

DATASHEET FOR CHECK VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/09

Sr. No.	Description	WAFER TYPE CHECK VALVE	SWING TYPE CHECK VALVE
		Specification	Specification
1. General			
1.1	Valve Size	2" and above	Vendor to furnish
1.2	Pressure Rating	150#/300#	150#/300#
1.3	Design Standard	API 6D	API 6D
1.4	Corrosion allowance		1.5 mm
2. Service Conditions			
2.1	Service	Natural Gas	Natural Gas
2.2	Design Pressure	1. For 150# - 19 Bar-g 2. For 300# - 49 Bar-g	1. For 150# - 19 Bar-g 2. For 300# - 49 Bar-g
2.3	Design Temperature	0°C to 65°C	0°C to 65°C
2.4	Operating Pressure Maximum	19 Bar-g for 150# application 49 Bar-g for 300# application	19 Bar-g for 150# application 49 Bar-g for 300# application
2.5	Operating Temperature	0°C to 50°C	0°C to 50°C
3. Valve Construction Design			
3.1	Location	Above Ground	Above Ground
3.2	Valve Type	Wafer Type	Swing Type
3.3	End Connections	Sandwich Type	Flange End (as per ASME B16.5) as per piping material specification.
3.4	Locking Arrangement	Not Applicable	Not Applicable
3.5	Shutoff Class	Class: IV	Class: IV
3.6	Flange Facing	RF-125 AARH (ASME B 16.5)	RF-125 AARH (ASME B 16.5)
4. Valve Material Specification (Equivalent Or Superior)			
	Part	Specified Material	Specified Material
4.1	Body	ASTM A 216 Gr WCB (Charpy test at 0°C)	ASTM A 216 Gr WCB (Charpy test at 0°C)



DATASHEET FOR CHECK VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/09

4.2	Stud and Nuts		Stud-ASTM A 193 Gr. B7 and Nut ASTM A 194 Gr. 2H, Hot Dipped Galvanized as per ASTM A 153
4.3	Body Gasket		Spiral Wound with inner & outer ring SS 316 with CNAF fill
4.4	Disc/ Plate	ASTM A 217 Gr. CA15	ASTM A 216 Gr. WCB + 13% Cr. Steel
4.5	Body Seat Ring	ASTM A 216 Gr. WCB + 13% Cr. Steel	ASTM A 216 Gr. WCB + 13% Cr. Steel
4.6	Disc Hinge	ASTM A 217 Gr. CA15/ SS316/ ASTM A 352 Gr. LCB	ASTM A 216 Gr. WCB + 13% Cr. Steel/ ASTM A 352 Gr. LCB/LCC + 13% Cr. Steel
4.7	Hinge Pin	ASTM A 479 Gr. SS410/ SS316	ASTM A 479 Gr. SS410/ SS316
4.8	Holder	SS 316	
4.9	Clip	SS 316	
4.10	Spring	SS 316/ Inconel X 750	SS 316
5. Valve Testing Requirement			
5.1	Hydrostatic Test	Body: 1.5 X Design Pressure Seat: 1.1 X Design Pressure	Body: 1.5 X Design Pressure Seat: 1.1 X Design Pressure
5.2	Charpy Impact Test	All pressure containing part as per the MOC standard In case Charpy test value not specified in relevant codes and standards than Charpy shall be carried out at 0 °C and absorbed energy value shall be average 35 J and minimum 28 J respectively.	All pressure containing part as per the MOC standard In case Charpy test value not specified in relevant codes and standards than Charpy shall be carried out at 0 °C and absorbed energy value shall be average 35 J and minimum 28 J respectively.
5.3	Hardness test	Applicable as per Material of construction standard	Applicable as per Material of construction standard
5.4	NDE Test	100% Radiography	100% Radiography
5.5	Marking & Painting	As per API 6D	As per API 6D/ MSS SP-25

Note:

1. Inspection and testing:

- Wafer Type Check Valve: As per this Data Sheet, GGL Specification, API 6D. Inspection shall be carried out by TPI at Manufacture's work as per QAP approved by GGL.



DATASHEET FOR CHECK VALVE CNG PRI, PRI, IPRS AND DRS (150# / 300# AND OPERATING TEMPERATURE 0 to 50 Deg C)

Document No.: GGL/TS/2021/JAN/09

- Swing Type Check Valve: As per this Data Sheet, GGL Specification, API 6D and API 598. Inspection shall be carried out by TPI at Manufacture's work as per QAP approved by GGL.
2. Short pattern valves are not acceptable.
 3. Vendor to submit GA drawing and QAP for approval prior to commencement of manufacturing.
 4. Test Certificates shall be reviewed by client/TPIA as per approved QAP, GA drawing, Inspection & Test certificates including NDE.
 5. In case valve is supplied in accordance with API 6D, Min. body valve thickness shall be as per ASME B 16.34 and corrosion allowance.